

CROCKMETER TEST DIN 55654

Comparison between our standard high gloss topcoat, and new developments.

The test has been carried out applying a force of 9N and doing 10 and 50 cycles with a 3M polishing paper 281Q as the rule DIN 55654 says.

Gloss(%)	Initial	after 50 cycles	after 50 cycles (recovered 24 hours)
A-024/C-024 50%	98%	73%	73%
A-050-10/C-050 100%	88%	83%	88%

